



TEST REPORT



98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-43-211-6144

FAX 82-43-211-6148

Report No : TAK-2018-032198
 Representative : HAN MYEUNG HO
 Company name : Hanwha L&C
 Address : 7_8F, CENTER1 Bldg, 26, Uljiro 5-gil, Jung-gu, Seoul, Korea
 Sample name : HANEX(S)

Receipt Date : 2018.02.21.
 Test Completion Date : 2018.03.13.

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Specific Gravity((23/23) °C)	-	-	1.82	ASTM D792-13(Method A)
Rockwell Hardness(HRM)	-	-	88	ASTM D785-08(2015)(Procedure A)
Tensile Strength	MPa	-	43.1	ASTM D638-14(*)
Tensile Modulus of Elasticity	GPa	-	12.1	ASTM D638-14(*)
Flexural Strength	MPa	-	65.3	ASTM D790-17(**)
Flexural Modulus of Elasticity	GPa	-	10.8	ASTM D790-17(**)
Izod Impact Strength	J/m	-	17	ASTM D256-10e1(Method A)
Water Absorption(24 h Immersion)	%	-	0.03	ASTM D570-98(2010)e1
Density(23 °C)	g/cm³	-	1.81	ASTM D792-13(Method A)
Heat Resistance(Appearance)	-	-	No Defects	JIS K 6902 : 2007(Method B)
Heat Water Resistance(Appearance)	-	-	No Defects	JIS K 6902 : 2007(Method B)
Deflection Temperature Under Load(1.82 MPa)	°C	-	106	ASTM D648-16(Method B)
Thermal Expansion	1/°C	-	3.5 × 10 ⁻⁵	JIS K 6911:1995

* Speed of Testing: 5 mm/min(Modulus: 1 mm/min), Specimen Type: Type I

** Speed of Testing: 4.9 mm/min, Support Span: 190 mm

- Usage of Report : QUALITY CONTROL

- Next Page -

Jungyuseok

Prepared by Jungyuseok
E-mail:jys1064@ktr.or.kr

You Seok

Reviewed by You Seok
Tel : 1577-0091(ARS ①→④)

2018.03.13

Korea Testing & Research Institute

President

Byun, Jong-Rip



QR Code for forgery



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-43-211-6144

FAX 82-43-211-6148

Report No : TAK-2018-032198

Receipt Date : 2018.02.21.

Representative : HAN MYEUNG HO

Test Completion Date : 2018.03.13.

Company name : Hanwha L&C

Address : 7_8F, CENTER1 Bldg, 26, Uljiro 5-gil, Jung-gu, Seoul, Korea

Sample name : HANEX(S)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

- Note :
- The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 - This test report shall be used only within the purpose of its defined usage and shall not be used fo public relation, advertisement and lawsuit.
 - This test report is olny valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Jungyuseok

Prepared by Jungyuseok

E-mail:jys1064@ktr.or.kr

You Seok

Reviewed by You Seok

Tel : 1577-0091(ARS ①→④)

2018.03.13

Korea Testing & Research Institute

President

Byun, Jong-Rip



QR Code for forgery